

No: Signafloor-01

Publishing Date: 01.01.2008 Revision Date/No: 26.04.2021/01

TECHNICAL DATA SHEET







SIGNAFLOOR - WHITE

MMA BASED FLOOR COATING PAINT

- •"Signafloor" two component floor coating paint is based on MMA resin. •This paint adheres to the surface with the reaction of components which are mixed at a certain rate.
- •Signafloor has high physical and chemical resistance, abrasion resistance and easy cleaning.
- •It can be used as top coat in multi-layer system or as self leveling. Film thickness can be applied between 1-4 mm.
- •Even under heavy traffic, it keeps its high durability far long time.
- •The paint should be applied within maximum 7 minutes after mixing the components each other.
- •Signafloor can be used far factories, plants, ware houses, parking areas, faod plants, hospitals, chemistry and pharmaceutical industries and all industrial floors.

PRODUCT INFORMATION

• Component A: MMA based floor coatting paint

• Component B: Hardener

• Application method: Please consult us.

• Product name: Signafloor

APPLICATION INFORMATION

Before the application of **Signafloor**, the area should be dry and away from dust, grease, and other dirt.

Use glove and mask during the application.

Surface Temperature: Between 10° C and 40 ° C

Maximum Humidity: %80

Dry Time: 20 min.(23 °C ve % 49 Humidity, 6 km/h wind)

PAINT CONSUMPTION AMOUNT

Paint 1,8 kg/m² for 1 mm

Note: The values in the table are theoretical values. Consumption amount can be changed according to the surface and weather conditions.

PHYSICAL PROPERTIES

• Color: White

Viscosity (KU): 110 ± 10
 Density: 1,80 g / ml. ± 0,1

RAL 9016 RAL 5015 RAL 1023 RAL 6001

RAL 9017 RAL 2004 RAL 3020 RAL 7040

RAL kataloğundan seçilen renk kodlarma göre istenilen renklerde üretilebilmektedir. [it can be produced according to the color codes selected from the RAL catalogue.



No: Signafloor-01 Publishing Date: 01.01.2008 Revision Date/No: 26.04.2021/01

TECHNICAL DATA SHEET

SIGNAFLOOR - WHITE

MMA BASED FLOOR COATING PAINT

PACKAGING AND STORAGE CONDITION

• Component A: 25 kg / Can • Component B: 25 kg / Can

- At proper storage conditions, shelf life is 1 year.
- Store at closed areas, and get away from fire sources.